



Commercial Black Neoprene Rubber

High resistance to mineral oils, greases, dilute acids and alkalis



- Good ageing and weathering properties, ideal for outdoor use.
- Hardwearing Neoprene is heat, chemical, oil, fire and ozone resistant.
- 65 degrees shore A hardness.
- Tensile strength at break: 6.0 Mpa.
- Elongation at break: 250%.

Parts

| Part Number | Size | Colour | Weight (kg) |
|-------------|-----------------------|--------|-------------|
| NES00001 | 1.4 m x 10 m x 1.5 mm | Black | 31 |
| NES00002 | 1.4 m x 10 m x 3 mm | Black | 61.4 |
| NES00003 | 1.4 m x 10 m x 4.5 mm | Black | 90.55 |
| NES00004 | 1.4 m x 10 m x 6 mm | Black | 125 |
| NES00005 | 1.4 m x 5 m x 10 mm | Black | 109 |
| NES00006 | 1.4 x 5 m x 12 mm | Black | 126.6 |
| NES00007 | 1.4 m x 5 m x 20 mm | Black | 236 |
| NES00008 | 1.4 m x 5 m x 25 mm | Black | 290 |

Technical Specifications

| | |
|--|--|
| Material | CR and SBR |
| Surface Finish | Smooth |
| Product Height | 1 mm-25 mm |
| Roll Length | 5 m, 10 m |
| Min. Operating Temperature | -20°C |
| Max. Operating Temperature | +80°C |
| Resistance to Chemicals | Effective resistance to mineral oils, greases, dilute acids and alkalis. |
| Typical Applications | Suitable for outdoor applications |
| Other Product Performance Information | Test Temperature 25°C Relative Humidity 35% Correlation criterion GB/T528-1998 GB/T3512-1989 GB/T531-1992 |
| COO (Country of Origin) | CN |

