




## Solid Fatigue-Step

Superior floor protection for your gym



- Easy install interlocking solid surface tiles.
- Ideal flooring for 'cross fit' style gyms.
- Absorbs the impact of heavy equipment such as free weights and medicine balls.
- Non porous rubber – sweat and other liquids cannot penetrate into the mat.
- Increases safety, as dropped equipment bounces and rolls less.
- Helps to reduce noise levels.
- Individual tiles can be moved and replaced with ease.
- Slip tested to DIN 51130.
- Easy to clean and maintain.
- High durability.
- Optional bevelled edging in yellow or black.



## Parts

Part Number	Size	Colour	Weight (kg)
ST010001	0.9 m x 0.9 m	Black	10.5
ST010001B1	0.9 m x 0.9 m	B1 Nitrile	10.5

## Technical Specifications

<b>Material</b>	Standard - Natural rubber with 20% NBR. Nitrile version - 35% NBR.
<b>Surface Finish</b>	Solid textured
<b>Product Height</b>	18 mm
<b>Min. Operating Temperature</b>	-20°C
<b>Max. Operating Temperature</b>	+130°C
<b>Resistance to Chemicals</b>	Standard version offers limited resistance to chemicals and oils. Nitrile version offers excellent resistance to oils and chemicals.

<b>Environmental Resistance</b>	Suitable for wet and dry environments. Will withstand welding splatter and spillages of other hot materials.
<b>UV Resistance</b>	Yes
<b>Typical Applications</b>	General industrial
<b>Installation Method</b>	Loose lay interlocking tiles
<b>Accessories</b>	Bevelled corner edges
<b>Cleaning Method</b>	Use of hard detergents not recommended
<b>Fire Tested to</b>	B1 version: BS EN 13501-1 Class Bfl - s1
<b>COO (Country of Origin)</b>	IN
<b>Storage and application</b>	Store at room temperature, free from deformations.
<b>Tensile Strength</b>	3.5 to 4 MPa
<b>Notes</b>	Silicone is used in the production process of the mats and a residue will possibly be left on the mat. This can be washed off using hot soapy water
<b>Slip Tested to</b>	DIN 51130 - R10

## Additional Information

- 
[Installation Guide](#)
- 
[Solid Fatigue Step Ramp Slip Test DIN 51130](#)
- 
[Solid Fatigue Step B1 Fire Test BS EN 13501](#)
- 
[Solid Fatigue Step B1 Fire Test EN ISO 9239](#)
- 
[Solid Fatigue Step B1 Fire Test EN ISO 11925](#)

Get in touch | To order FREE samples or arrange a site visit please call +44 (0)1788 228 555 or email [sales@cobaeurope.com](mailto:sales@cobaeurope.com)

[www.cobaeurope.com](http://www.cobaeurope.com)